

PRO-SET®

Technical Data XR29A~M2046

FIRE RETARDANT LAMINATING EPOXY

COMBINED FEATURES

Medium viscosity for good wet out of all synthetic composite fabrics and core materials.

Thixotroped to prevent drain out in heavy fabrics and on vertical surfaces.

High tack to help hold heavy fabric and core in place on vertical surfaces.

Fire retardant system (listed as XR02-099-29A) is accepted for compliance with Lloyd's Register Rules and Regulations and with the International Convention for Safety of Life at Sea (SOLAS), 1974, as amended, for use on ships and offshore installations classed with Lloyd's Register, and for use on ships and offshore installations when authorized by contracting governments to issue the relevant certificates, licenses, permits, etc.

Elevated temperature cure is required; thermal and mechanical properties suitable for composite components and high temperature tooling and molds.

T_g as high as 149° F (65°C) with proper post cure providing excellent temperature stability and great part cosmetics.

Shelf life is 3 years for resin and 2 years for hardener when properly stored².

Caution- *Stir Resin thoroughly with mechanical mixer before blending with Hardener. Contents may settle during storage.*

The New
Standard

EPOXIES for
Laminating
Infusion
Tooling
Assembly

Gougeon Brothers, Inc.
P.O. Box 908
Bay City, MI 48707
prosetepoxy.com
888-377-6738

ISO9001:2015 Certified

Rev 2 / Dec 2015

©2018 Gougeon Brothers, Inc.

HANDLING PROPERTIES

Property	Standard	Units	72°F (22°C)
100g Pot Life	ASTM D2471	minutes	225-275
Viscosity Mixed	ASTM D2196	cP	1,000
Viscosity (resin)	ASTM D2196	cP	1,375
Viscosity (hardener)	ASTM D2196	cP	115

MIX RATIO

Method	Resin:Hardener	Resin:Hardener
Weight	3.85:1	100:26.0
Volume	3.23:1	100:31.0

DENSITY

State	Units	72°F (22°C)
Resin	lb/gal (g/cc)	9.51 (1.14)
Hardener	lb/gal (g/cc)	8.10 (0.97)

MECHANICAL PROPERTIES

Property	Standard	Units	RT Gelation + 140°F (60°C) x 8 hrs
Hardness	ASTM D2240	Type D	84
Compression Yield	ASTM D695	psi (MPa)	10,430 (72)
Tensile Strength	ASTM D638	psi (MPa)	8,040 (55)
Tensile Modulus	ASTM D638	psi (MPa)	4.14E+05 (2854)
Tensile Elongation	ASTM D638	%	3.9
Flexural Strength	ASTM D790	psi (MPa)	14,000 (97)
Flexural Modulus	ASTM D790	psi (MPa)	4.27E+05 (2944)

THERMAL PROPERTIES

Property	Standard	Units	RT Gelation + 140°F (60°C) x 8 hrs
T _g DSC Onset-1st Heat	ASTM E1356	°F (°C)	127 (53)
Heat Deflection Temperature	ASTM D648	°F (°C)	124 (51)
Ultimate T _g by DSC	ASTM E1356	°F (°C)	149 (65) ¹

¹ Additional post cure may be required; contact Technical Department for details.

² Store PRO-SET® Epoxy resins and hardeners at room temperature in sealed containers until shortly before use. As with many high-performance epoxy resins, repeated exposure to low temperatures during storage may cause the resin to crystallize. If this occurs, warm the resin to 125° F and stir to dissolve crystals. Hardeners may form carbamation when exposed to CO₂ and moisture in the atmosphere for extended periods of time. Prevent carbamation by protecting hardeners from exposure until immediately prior to processing.

Test specimens were neat epoxy
(without fiber reinforcement).
Typical values, not to be construed
as specification.

PRODUCT TYPE: SURVIVAL CRAFT MATERIAL
SPECIFIED: SOLAS Chapter III as revised 1996, Regulations 4 and 34.
LSA Code, Regulations 1.2, 2.1, 4.3, 4.4 and 5.1
IMO Resolution MSC 81(70) Part 1.
IMO Circular MSC / Circ. 1006
CERTIFICATE NO. SAS S030031
ISSUED BY: Lloyd's Register of Shipping, London.
DATE OF ISSURE: 24 March 2003.